



TECHNICAL DATA SHEET No 218

BODY 691 CLEAR UHS SR 2:1

GENERAL TECHNICAL DESCRIPTION

Ultra high solid clear coat suitable for full body, partial or spot panel repairs.

Great gloss retaining.

High mechanical and chemical resistance.

Excellent leveling.

SURFACE

HB BODY solvent- and waterborne basecoat paints

PRETREATMENT/CLEANING OF SUBSTRATE



Let the basecoat dry sufficiently before the clearcoat. Clean the surface from the dust with a tack cloth.

PRODUCT APPLICATION:



Mix 2 parts CLEAR COAT with 1 part H754 FAST / H753 NORMAL / H752 SLOW HARDENERS FOR TOPCOATS
Pot life at 23°C (73°F):
- H752 / H753: 3.5 h
- H754: 2.5 h



Addition 10 - 20% 740 NORMAL / 741 SLOW ACRYL THINNER / REDUCER



Ready to spray: 16 - 17 s
DIN 4 / 20°C (68°F)



1.2 - 1.3 mm
1.7 - 2.2 bar (25 - 32 psi)
2x coats = 50 - 60 µm
(2 - 2.4 mil)



10 - 15 min / 23°C (73°F)
Flash off time between coats
15 - 20 min / 23°C (73°F)
Flash off time before drying



25 - 30 min / 60°C (140°F)
panel temperature
20 - 24 h / 23°C (73°F)



Short wave 10 - 15 min
Distance: 60 - 70cm

TEMPERATURE	PARTIAL REPAIR	FULL REPAIR
15-20°C (59-68°F)	H754 +10-20% 740 H753 +10-20% 740	H753 +10-20% 740
20-25°C (68-77°F)	H754 +10-20% 740 H753 +10-20% 740	H753 +10-20% 740
25-30°C (77-86°F)	H754 +10-20% 740 H754 +10-20% 741 H753 +10-20% 740 H752 +10-20% 740	H753 +10-20% 740 H753 +10-20% 741 H752 +10-20% 740
>30°C (86°F)	H753 +10-20% 740 H752 +10-20% 740	H752 +10-20% 740 H752 +10-20% 741

SPECIFIC GRAVITY0.98 ± 0.01 g/cm³**SOLID CONTENT**

50 ± 2 % Weight

VOC (2004/42/EC)

This is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 840 g/L. 2004/42/IIIB(e)(840)840

CLEANING OF EQUIPMENT

Clean after final use with 740 ACRYL NORMAL or 767 NITRO thinner / reducer

REMARKS

- Application only with the recommended hardeners and thinners / reducers.
- Do not use at temperatures below 15°C (59°F).

STORAGE SHELF LIFE

Guaranteed shelf life of 24 months in unused original containers stored in a cool place (5 - 25°C) (41 - 77°F).



Always wear protective equipment



Follow the application instructions mentioned in this TDS

2K paint systems tend to react with water, hence all the equipment used must be moisture free. Isocyanates may cause skin sensitization. More specifically, care should be taken when handling the material. Anyone with a history of histaminic conditions, or respiratory problems should consult the doctor first.

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

MAY 2025